ULTRAL **EPDM 150G**

EPDM Waterproofing and Vapor Barrier Membrane

Conforms to ASTM D 4637 and ASTM D 6134

ULTRAL EPDM 150-G is a Ethylene Propylene Diene Monomer (M) weather proofing membrane designed for long-term performance waterproofing system application. ULTRAL EPDM 150-G membrane is a lightweight, durable and weatherproof single-ply waterproofing membrane perfect for a wide variety of applications. Properly designed, installed, and maintained EPDM systems can successfully withstand extreme weather cycles. For more than 3 decades ,ULTRAL EPDM 150-G have proven that it can withstand extreme temperature fluctuations and constant exposure to direct sunlight. Also, it has exceptional elasticity and will not split or crack under normal building movement.



Features

- Excellent Weatherability
- UV resistant and Highly Durable
- Impermeable to water and highly resistant to moisture and vapour
- Completely echo friendly, suitable for interior and exterior applications
- High resistance to ozone, weathering and abrasion
- Flexibility in low temperatures
- Superior resistance to extreme heat
- Thermal shock durability
- 100 % Green Building comply product

Field of Application

- Building envelope and protection
- Façade and Curtain wall
- Substructure, Superstructure and Roof
- Skylights and expansion joints
- Storage facilities, bridges and tunnels
- Oil and gas & Infra projects

engineered to perform

ULTRAL EPDM 150G Confirms to ASTM D 4637

#	PROPERTY	TEST STANDARD	SPECIFIC VALUES
1	Thickness of the sheet		1.52 mm
2	Specific Weight,kg/m³		1.2
3	Tensile Strength, min, MPa	ASTM D 412	≥ 9.0
4	Tear strength, min, kN/m	ASTM D 624	35
5	Elongation at break %	ASTM D 412	≥350
6	Factory seam strength, Min, kN	ASTM D 816	9.1
7	Brittleness Temperature, °C	ASTM D 746	-45
8	UV resistance 168 hours at 45°C	ASTM D 1149	No cracks
9	Resistance to water absorption, Change in mass, max, after 172 hours immersion@70°C,%	ASTM 471	+8,-2
10	Resistance to out door (UV) weathering Xenon Arc, 7560kj/m² irradiance, 80°C black panel temp.	ASTM D 151	No cracks
11	Polymer (EPDM) content %	ASTM D 297	100
12	Water Vapor Permeability, max, perms	ASTM E 96(Proc B or BW)	0.10

RESISTANCE TO HEAT AGING

(Properties after 172 hours exposure @118°C) ASTM D 573

1	Tensile Strength, min, MPa	ASTM D 412	9
2	Elongation at break %	ASTM D 412	205

SYSTEMS

- Mechanically fastened system combines sound & durable quality with simple and easy installation. Loosely lay the EPDM membrane on top of concrete roof .Then secure it with termination bar and fastener.
- Fully-adhered system conforms to the idea of fully bonded installation. It is recommended for irregular building configurations, slopes, walls, etc. Adhere the EPDM membrane directly to the smooth and clean substrate .
- Ballasted system is specially designed for low-storey buildings which have wide, flat roof decks and for supporting heavy loads. Loosely lay the EPDM membrane over the substrate. Then, cover the membrane with gravels
- Loose laid System for pond lining and lake waterproofing systems

PACKING

LENGTH :10 M/ 20 M : WIDTH 1.2 / 1.5

STORAGE AND SAFETY

Store in a covered place and read ORGANIX MSDS of ULTRAL EPDM prior to the application

engineered to perform

Organix Building System LLC
Dubai – United Arab Emirates
Email : info@organixbs.com
www.organixbs.com